

AXMINSTER STANDARD BROADLOOM SPECIFICATIONS

Pile Yarn	80% Wool 20% Nylon				
Pile Height	6.35 mm				
Yarn Count	R620 Tex / 2				
Backing Materials	Polyester, Polypropylene, SBR Latex, Jute				
Width	3,66 & 4,00 mtr				
	METHOD	7 ROW	8 ROW	9 ROW	10 ROW
Pitch per 10 cm	ISO 1763	27,6	27,6	27,6	27,6
Rows per 10 cm	ISO 1763	27,6	31,5	35,4	39,4
Tufts per 100 cm ²	ISO 1763	760	870	980	1080
Pile height (mm)	ISO 1766	6,35	6,35	6,35	6,35
Total Thickness (mm)	ISO 1765	9,0	9,0	9,0	9,0
Surface Pile mass (g/m ²)	ISO 8543	646	738	830	925
Total Pile mass (g/m ²)	Calculated	881	1006	1130	1250
Total Mass (g/m ²)	ISO 8543	1550	1650	1700	1850
Use Class	SANS 1375-2005	Class 3	Class 4	Class 5	Class 5
Fire Index Class	SANS 10177-P4	Class 2	Class 2	Class 2	Class 2

NOTE: Normal Textile tolerances apply. We reserve the right to amend specifications without notice with no detrimental effect on performance.